


Exova Warringtonfire
Holmesfield Road
Warrington
WA1 2DS
United Kingdom

T : +44 (0) 1925 655116
F : +44 (0) 1925 655419
E : warrington@exova.com
W : www.exova.com



BS EN ISO 11925-2: 2010



Ignitability Of Building Products Subjected To Direct Impingement Of Flame Part 2: Single Flame Source Test

A Report To: Cladco Profiles Ltd.

Document Reference: 397800

Date: 15th May 2018

Issue No.: 1

Page 1

Testing
Advising
Assuring



Executive Summary

Objective To determine the performance of the following product when tested in accordance with BS EN ISO 11925-2:2010.

Generic Description	Product reference	Thickness	Weight per unit area
Composite comprising 50% hardwood and 50% polyethylene	"Cladco Hollow Composite Decking"	25mm	17.94kg/m ² *
*determined by Exova Warringtonfire			
Please see page 6 of this test report for the full description of the product tested			

Test Sponsor Cladco Profiles Limited, North Road Industrial Estate, North Road, Okehampton, Devon, EX20 1BQ

Test Results: On the set of six specimens which were subject to surface application, the maximum flame height reached was observed to be 0mm.

On the set of six specimens which were subject to edge application, the maximum flame height reached was observed to be 20 ± 0.8mm

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a coverage probability of approximately 95%. The uncertainty evaluation has been carried out in accordance with UKAS requirements.

Date of Test 25th April 2018

Signatories



Responsible Officer
C Jacques*
Technical Officer



Authorised
S. Deeming *
Business Unit Head



Approved
T. Mort *
Senior Technical Officer

* For and on behalf of **Exova Warringtonfire**.

Report Issued: 15th May 2018

This version of the report has been produced from a .pdf format electronic file that has been provided by Exova Warringtonfire to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of Exova Warringtonfire.

CONTENTS	PAGE NO.
EXECUTIVE SUMMARY	2
SIGNATORIES.....	2
TEST DETAILS.....	4
DESCRIPTION OF TEST SPECIMENS	5
TEST RESULTS	6
TABLE 1	7
TABLE 2	7
REVISION HISTORY	8



Test Details

Purpose of test	<p>To determine the performance of specimens of a product when they are subjected to the conditions of the test specified in BS EN ISO 11925-2:2010 "Reaction to Fire tests - Ignitability Of Building Products Subjected to Direct Impingement of Flame – Part 2: Single Flame Source Test".</p> <p>The test was performed in accordance with the procedure specified in BS EN ISO 11925-2:2010 Reaction to Fire Tests - Ignitability of Building Products subjected to direct impingement of flame – Part 2: Single Flame Source Test, and this report should be read in conjunction with that BS EN ISO Standard.</p>
Scope of test	BS EN ISO 11925-2 specifies a method of test for determining the ignitability of building products by direct small flame impingement under zero impressed irradiance using specimens tested in a vertical orientation.
Fire test study group/EGOLF	Certain aspects of some fire test specifications are open to different interpretations. The Fire Test Study Group and EGOLF have identified a number of such areas and has agreed Resolutions which define common agreement of interpretations between fire test laboratories which are members of the Groups. Where such Resolutions are applicable to this test they have been followed.
Instruction to test	The test was conducted on the 25 th April 2018 at the request of Cladco Profiles Ltd., the sponsor of the test.
Provision of test specimens	The specimens were supplied by the sponsor of the test. Exova Warringtonfire was not involved in any selection or sampling procedure.
Conditioning of specimens	<p>The specimens were received on the 22nd March 2018.</p> <p>Prior to test the specimens were stored for 34 days in a standard atmosphere as defined in BS EN 13238:2010 Conditioning Procedures and General Rules for selection of substrates until constant mass was achieved.</p>
Intended application	Flooring
Substrate	The specimens were tested with an 8mm thick fibre cement board substrate (as specified in EN 13238: 2010) present.
Flame application time	The flame was applied for 15 seconds

Description of Test Specimens

The description of the system given below has been prepared from information provided by the sponsor of the test. This information has not been independently verified by **Exova Warringtonfire**.

All values quoted are nominal, unless tolerances are given.

Generic type	Composite comprising 50% hardwood and 50% polyethylene
Product reference	"Cladco Hollow Composite Decking"
Name of manufacturer	
Thickness	25mm (stated by sponsor) 24.3mm (determined by Exova Warringtonfire)
Weight per unit area	17.94kg/m ² (determined by Exova Warringtonfire)
Colour reference	"Brown" (observed by Exova Warringtonfire)
Flame retardant details	See Note 1 below
Brief description of manufacturing process	See Note 2 below

Note 1. The sponsor of the test has confirmed that no flame retardant additives were utilised in the production of the product.

Note 2. The sponsor of the test is unable to provide this information.

Test Results

Number of specimens tested

Six specimens were tested, each of which were subjected to surface exposure to flame with the decorative face exposed.

Six specimens were tested, each of which were subjected to edge exposure to flame with the decorative face exposed.

Applicability of test results

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which they were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any product which is supplied or used is fully represented by the specimens which were tested.

The test results for the individual specimens, together with observations made during the test and comments on any difficulties encountered during the test are given in Tables 1 and 2.

On the set of six specimens which were subject to surface application, the maximum flame height reached was observed to be 0mm.

On the set of six specimens which were subject to edge application, the maximum flame height reached was observed to be 20 ± 0.8 mm

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a coverage probability of approximately 95%. The uncertainty evaluation has been carried out in accordance with UKAS requirements.

Validity

The specification and interpretation of fire test methods are the subject of ongoing development and refinement. Changes in associated legislation may also occur. For these reasons it is recommended that the relevance of test reports over five years old should be considered by the user. The laboratory that issued the report will be able to offer, on behalf of the legal owner, a review of the procedures adopted for a particular test to ensure that they are consistent with current practices, and if required may endorse the test report.

This report may only be reproduced in full. Extracts or abridgements shall not be published without permission of **Exova Warringtonfire**.

Table 1
Test Flame Application Position - Surface Of The Decorative Face

Specimen No.	Ignition Yes/No	Time from start of test for flame tip to reach 150mm (seconds)	Extent of Flame Spread (± 1.7 mm)	Flaming Debris	Glowing	Extent of Damaged Area (mm)	
						Height	Width
1	No	Did not reach	Nil	None	None	31	28
2	No	Did not reach	Nil	None	None	28	19
3	No	Did not reach	Nil	None	None	27	18
4	No	Did not reach	Nil	None	None	28	19
5	No	Did not reach	Nil	None	None	25	19
6	No	Did not reach	Nil	None	None	28	17

Table 2
Test Flame Application Position - Edge Of The Decorative Face

Specimen No.	Ignition Yes/No	Time from start of test for flame tip to reach 150mm (seconds)	Extent of Flame Spread (± 0.8 mm)	Flaming Debris	Glowing	Extent of Damaged Area (mm)	
						Height	Width
1	Yes	Did not reach	10	None	None	43	40
2	Yes	Did not reach	10	None	None	32	30
3	Yes	Did not reach	10	None	None	30	28
4	Yes	Did not reach	20	None	None	24	21
5	Yes	Did not reach	10	None	None	19	19
6	Yes	Did not reach	10	None	None	21	20

Revision History

Issue No :	Re-issue Date :
Revised By:	Approved By:
Reason for Revision:	

Issue No :	Re-issue Date :
Revised By:	Approved By:
Reason for Revision:	